

SIBERIAN LARCH

AB: Mostly sound knots, occasional black knots, knotholes and shakes are professionally filled, occasional pith ray, occasional resin pockets, no sapwood, slight compression wood and slight colour variations, jointfree gluing.

Bottom layer standard: closed jointing, no blue-stain.



Characteristics

The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.

STIA Norm	Thickness mm app.	Length mm (Width 2030)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AB/ST	15	5000	5	114/120/128/137	BML Larch	35
AB/ST	19	5000	5	114/120/128/137	SML Larch	30
AB/ST	24	5000	5	114/120/128/137	SML Spruce	25
AB/ST	27	5000	5	114/120/128/137	SML Larch	20
AB/ST	42	5000	5	114/120/128/137	SML Spruce	10

SWP/3 non structural (ns): Solid wood panels for non-structural use in wet areas with regard to constructive wood protection also for exterior use = **AW100**. **Legend:** SML = strip core, BML = board middle layer.