

# SPRUCE

**AB:** Mostly sound knots, occasional small filled knots and small filled knotholes, no colour defects, occasional pith ray possible, no shakes, small resin pockets possible, slight compression wood and slight colour variations might occur, jointfree gluing.

**Bottom layer standard:** closed jointing, no blue-stain.

**Bottom layer AB:** as above.

This panel is also available with a gluing adapted to wet areas (sauna) and is therefore in accordance with the emission requirements according to ONORM M6219-1:2010 for the use in sauna areas (see information "Admonter Element's in sauna areas" at <http://www.admonter.at/en/downloads/>).



The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.

STIA Norm	Thickness mm app.	Length mm (Width 2030)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AB/ST	12	5000	3,6	114/137/142/146	BML Spruce	25
AB/ST	15	5000	3,6	114/137/142/146	SML Spruce	35
AB/AB	19	5000	6	114/137/142/146		30
AB/ST (adapted to sauna areas)	19	5000	6	114/137/142/146	BML/SML Spruce (subject to availability)	30
UNI/C+	19	5000	6	171		
AB/ST	22	5000	6	114/137/142/146	SML Spruce	25
AB/ST	24	5000	6	114/137/142/146	SML Spruce	25
AB/AB	27	5000	9	114/137/142/146	BML/SML Spruce	20
AB/ST	27	5000	9	114/137/142/146	BML/SML Spruce (subject to availability)	20
AB/ST	42	5000	6	114/137/142/146	SML Spruce	10

**SWP/3 non structural (ns):** Solid wood panels for non-structural use in wet areas with regard to constructive wood protection also for exterior use = **AW100**. **Legend:** SML = strip core, BML = board middle layer.



# SPRUCE HACKED H1

**UNI:** bigger knots and more rustic appearance due to wider width of top layers. Mostly sound knots, occasional small knots, small filled knotholes, occasional with ray possible, no shakes, small resin pockets possible, slight compression wood and slight colour variations might occur, jointfree gluing.

**Bottom layer C+:** no special quality specification, holes are filled.

**Surface:** hacked - holes generated by this surface treatment are not filled (visible middle layer).



The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.

STIA Norm	Thickness mm app.	Length mm (Width 2030)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
UNI/C+	19	5000	6	171	BML/SML Spruce (subject to availability)	30

**SWP/3 non structural (ns):** Solid wood panels for non-structural use in wet areas with regard to constructive wood protection also for exterior use = **AW100**.

**Legend:** SML = strip core, BML = board middle layer.