

AMERICAN WALNUT



Initial care - with Admonter maintenance oil

You can find more information in the Admonter care- and laying instructions and at www.admonter.eu/en/downloads/



Admonter Natural Floor on under-floor-heating-system

Admonter Natural Floors are ideally suited for under-floor heating systems. We recommend hot-water underfloor heating systems set at low temperature. The surface temperature of 29°C must not be exceeded. Beech is not suitable for under-floor heating systems! We suggest that our products ideally are fully glued down for best results with Admonter elastic adhesive. However, like all engineered boards our planks can be laid as a floating installation (except 2-layer floors and 3-layer floors small (SF-RS), they have to be fully glued down).

More information at www.admonter.at or contact your specialist dealer.

Skirting: Typ1, Typ2, Typ3 white, Typ4

Grading	Thickn. mm	Width mm	Length mm	Installation and construction			Surface	Texture
				Tongue & groove		lock-it		
elegance	10	100/120	1000/1200	2-layer	-	-	ng, uv	sanded
	10	158	2000	-	-	2-layer	natural oil	sanded
	10	192	2000	-	-	2-layer	natural oil	sanded
	13	120	1200	-	-	3-layer SF-RS	ng, uv, ml	sanded
	15	138	1850/2000	-	3-layer NH-RS	-	ng, uv, ml	sanded
	15	158	1850/2000	3-layer LH-RS	3-layer NH-RS	3-layer NH-RS	ng, uv, ml	sanded
rustic	15	192	1850/2000	3-layer LH-RS	-	-	ng, uv, ml	sanded
	10	158	2000	-	-	2-layer	natural oil	sanded
	10	192	2000	-	-	2-layer	natural oil	sanded
	15	138	1850/2000	-	3-layer NH-RS	-	ng, uv, ml	sanded, antico
	15	158	1850/2000	-	3-layer NH-RS	3-layer NH-RS	ng, uv, ml	sanded, antico
15	192	1850/2000	-	3-layer NH-RS	-	ng, uv, ml	sanded, antico	

Please note: antico surface texture: available with ng + tongue & groove + 3-layer NH-RS

Technical information

Wood species	Thickness mm	Weight (kg/m ²)	Moisture content (%)	Lambda	d-Value	Hardness	Fire classification
American Walnut**	10	5,5 / 5,9	7+/-2 / 7+/-2	0,16 / 0,16	0,063 / 0,069	36 / 36	C _{fl} -s1
American Walnut	13	6,9	7+/-2	0,15	0,087	36	C _{fl} -s1
American Walnut*	15	7,9 / 7,7	7+/-2 / 7+/-2	0,17 / 0,16	0,088 / 0,094	36 / 36	C _{fl} -s1

LH-RS: Hardwood-backing / NH-RS: Softwood-backing
SF-RS: Softwood-veneer-backing, ng: natural oiled / uv: UV oiled / ml: matt lacquer
* LH-RS / NH-RS ** Length 1000 or 1200 mm / Length 1850 or 2000 mm



For more information visit our website www.admonter.at