

OAK DARK



Initial care - with Admonter maintenance oil

You can find more information in the Admonter care- and laving instructions and at www.admonter.eu/en/downloads/

Admonter Natural Floor on under-floor-heating-system

Admonter Natural Floors are ideally suited for under-floor heating systems. We recommend hot-water underfloor heating systems set at low temperature. The surface temperature of 29°C must not be exceeded.



The only exception is Beech. We suggest that our products ideally are fully glued down for best results with Admonter elastic adhesive. However, like all engineered boards our planks can be laid as a floating installation (except 2-layer floors and 3-layer floors small (SF-RS), they have to be fully glued down).

More information at www.admonter.at or contact your specialist dealer.

Skirting: Typ1, Typ2, Typ3 white, Typ4

Grading	Thickn. mm	Width mm	Length mm	Installa	ation and const	Surface	Texture	
				Tongue & groove		lock-it	Surface	Texture
noblesse	15	154	1850/2000	-	3-layer NH-RS	3-layer NH-RS	ng, uv, ml	sanded, brushed
	15	188	1850/2000	-	3-layer NH-RS	-	ng, uv, ml	sanded, brushed
basic	10	100/120	1000/1200	2-layer	-	-	ng, uv	sanded, brushed
	13	118	1200	-	-	3-layer SF-RS	ng, uv, ml	sanded, brushed
	15	154	1850/2000	-	3-layer NH-RS	3-layer NH-RS	ng, uv, ml	sanded, brushed
	15	188	1850/2000	-	3-layer NH-RS	-	ng, uv, ml	sanded, brushed
rustic	15	154	1850/2000	-	3-layer NH-RS	-	natural oil	antico
	15	188	1850/2000	-	3-layer NH-RS	-	natural oil	antico

Technical Information											
Wood species	Thickness mm	Weight (kg/m²)	Moisture Lambda		d-Value	Hardness	Fire classification				
Oak dark	10	5,8	5+/-2	0,15	0,067	39	C _{ff} -s1				
Oak dark	13	7,1	5+/-2	0,14	0,094	39	C _{fl} -s1				
Oak dark	15	8,4	5+/-2	0,14	0,107	38	C _{ff} -s1				

LH-RS: Hardwood-backing / NH-RS: Softwood-backing

SF-RS: Softwood-veneer-backing, ng: natural oiled / uv: UV oiled / ml: matt lacquer
*LH-RS / NH-RS ** Length 1000 or 1200 mm / Length 1850 or 2000 mm















